

POLYSEAL PS PG

2 part pouring grade polysulphide joint sealant

TDS_Polyseal-PS-PG_GCC_0910

1

POLYSEAL PS PG is a two component pourable, self leveling polysulphide resin based joint sealant. POLYSEAL PS PG is specifically designed to be used as a watertight seal for moderate movement and control joints in horizontal areas. It is based on a liquid polysulphide polymer which when mixed with the hardener, cures to form a tough, flexible and non staining rubber like seal. POLYSEAL PS PG has excellent adhesion to concrete, stone, metals and other common building surfaces. The cured sealant has good resistance to most environmental chemicals & resists deterioration on prolonged exposure to UV.

POLYSEAL PS PG is suitable for use in horizontal areas with a maximum slope gradient of 10%.

CHARACTERISTICS

- ▶ Highly resilient with excellent recovery characteristics
- ▶ Provides permanent and uniform watertight seal
- ▶ Non-staining
- ▶ Excellent resistance to fatigue and stays flexible throughout its service life—won't become brittle, caulk or crack due to ultra violet exposure
- ▶ Prevents uncontrolled cracking by allowing expansion and contraction during temperature changes
- ▶ Excellent adhesion to most common building substrates
- ▶ Good resistance to ageing. Retains joint soundness once cured
- ▶ Resistance against mild chemicals, hydrocarbon fuels, sea water
- ▶ Non-toxic. Can be used in potable water applications, swimming pools

FIELDS OF APPLICATION


Sealing of movement and control joints in:

- ▶ Structural floor joints
- ▶ Airport runways and apron pavements
- ▶ Industrial warehouses
- ▶ Garages & workshops
- ▶ Swimming pool floors

APPLICATION INSTRUCTIONS

Joint preparation

The joint surface must be clean, dry and free from oil, loose particles, cement laitance and other contaminants which may affect the adhesion. A thorough wire brushing, grinding, sand blasting or solvent cleaning may be required to expose a clean and sound substrate. The compressible joint filler shall be cut back to expose a uniform joint depth.




For illustration Purpose only

Priming

Primer should be applied to clean, dry surface prior to the installation of backer rod or bond breaking tape. POLYPRIME PS* is recommended to be applied on porous substrates. For non-porous substrates such as steel or glass, use POLYPRIME NP* for optimum adhesion. The primer shall be applied by a brush in a thin coat application and shall be allowed to become tack free prior to the application of the sealant.

The joint edges shall be re-primed if the sealant installation is not carried out within 3 hours of application of the primer. For obtaining a clean and

neat finish, masking tape shall be applied on both the edges of the groove before applying the primer.




For illustration Purpose only

Back-Up Material

A bond breaking backing rod (POLYROD)* shall be inserted into all movement joints to avoid a three sided adhesion. Use of a backing rod will ensure proper joint depth and at the same time facilitate the formation of an hour glass profile on the applied sealant. The backer rod will also provide resistance to sealant tooling pressure and help to attain proper wetting of the substrate when the sealant is being tooled. The backing rod being inserted into the joint shall be of a diameter which is at least 20% larger but not greater 33% of the joint width. This will ensure that the backer rod remains in compression and in place during sealant installation. For static and joints where the depth is not sufficient for the use of the backing rod, a bond breaking tape may be applied to prevent the three side adhesion.

CAUTION: Do not damage or poke holes in the backer rod during or after installation, since this may cause air bubbles in the sealant and affect its performance.



For illustration Purpose only

MIXING & APPLICATION

POLYSEAL PS PG is supplied in pre-weighted two parts pack which requires on site mixing. Pour the hardener (Part B) into the base (Part A) pail and mix thor-

oughly with a slow speed drill (300-400 rpm) fitted to a flat bladed paddle for 8-10 minutes till a uniform colour and consistency is achieved.

DO NOT PART MIX. Since the base and the curing agent ratio controls the ultimate physical properties like adhesion, durability and strength, one complete kit has to be mixed at a time. The side and base of the container shall be periodically scrapped with a scrapper to ensure that the curing agent is properly dispersed and blended in the mix. Pour the mixed material directly into the joint from the pail. Once the sealant has been installed a suitable rounded tool soaked in soapy water can be used to achieve an hour glass profile. Any masking tape applied should be removed immediately after the sealant is installed.



For illustration Purpose only

LIMITATIONS

POLYSEAL PS PG is not recommended for:

- ▶ Vertical joints
- ▶ Movement joints having MAF >25%
- ▶ Damp and contaminated surfaces
- ▶ Asphalt pavements
- ▶ Over painting (paint compatibility with sealant shall be checked prior to painting)
- ▶ Joints >50mm width



For illustration Purpose only

JOINT DESIGNS

The width of the joint should be a minimum of 4 times the anticipated movement. Joints with cyclic movement should have a width to depth ratio of 2:1 for butt joints and 1:1 for floor, static and lap joints. The joint depth shall not exceed the width.

The joint width and depth should be maintained as recommended:

Joint Width

- ▶ 6 mm (Minimum)
- ▶ 30 mm (Maximum)

Joint Depth

- ▶ 6 mm (Minimum for porous surfaces)
- ▶ 5 mm (Minimum for non porous surfaces)
- ▶ 20mm for heavily trafficked floor joints and areas exposed to hydrostatic pressure



For illustration Purpose only

3

CLEANING

Remove all excess sealant with a scraper. Any spillage can be cleaned using **POLYSOLVENT***. Clean all tools and equipments using similar solvent immediately after the tooling. Hardened materials can be removed mechanically only.

COVERAGE

Length of joints in meters filled per 1 lt of **POLYSEAL PS PG**

Depth [mm]	Width [mm]							
	6	10	15	20	25	30	40	50
6	27.5	16.5						
10		10	6.5	5				
15			4.4	3.3	2.6	2.2		
20				2.5	2.0	1.6	1.25	
25					1.6	1.3	1	0.8
30						1.1	0.83	0.67
40							0.62	
50								

Calculation based on theoretical coverage. Actual material consumption at site will vary depending on the wastage.

MAINTENANCE

If the Sealant is damaged but the bond is intact, cut out the damaged area and recaulk. If the bond has been affected, remove the sealant completely. Clean and prepare the joint in accordance with instructions under "Joint Preparation" and recaulk.

STANDARDS

POLYSEAL PS PG complies with the requirements of: BS 4254

BS 5212: Part 1,

WRAS- BS 6920 Test on effect of water quality, ASTM C 920, Type M, Grade P, Class 25, USE T

STORAGE & SHELF LIFE

Store in a cool, dry place and keep away from all sources of heat and sunlight. In tropical climates, store in air condition rooms. The shelf life is up to 12 months in un-opened condition and if stored as per recommendations. Excessive exposure to sunlight, humidity and UV will result in the deterioration of the quality of the product and reduce its shelf life.

DISPOSAL

Mix separate product components in ratio and as supplied in suitable metal containers. Allow the mix to cure completely. Dispose as hazardous waste. It is recommended to use licensed waste disposal contractors and consult the local authority regarding the regulations

HEALTH & SAFETY

As with all construction chemical products caution should be exercised. Contains manganese dioxide. Which is corrosive and may cause burns to skin if handled without proper protection. Refer the product MSDS for full details.

Protective clothing such as gloves and goggles should be worn. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

TECHNICAL SPECIFICATION

PROPERTIES	VALUES
Color	Grey
Density, [g/cc]	1.3±0.05
Viscosity	Free flowing
Shrinkage	Negligible
Application life [min]	> 120
MAF [%]	±25
Shore 'A' Hardness	15-30
Tack free time [hrs]	5
Adhesion to concrete, [N]	>25
Tensile strength, [Psi]	>50
Elongation, [%]	>300
UV resistance @300 hrs	No Deterioration
Water potability [WRC]	Passes
Chemical resistance	pH 2.5 to 11.5, Hydrocarbon fuels, vegetable oil,urea, seawater
Cracking & Chalking after heat ageing @70°C	No Deterioration
Initial cure @ standard conditions,[hrs]	24
Final cure @standard conditions, [days]	7
Application temp,[°C]	+5 to +45
Service temp,[°C]	-20 to +80

All values given are subject to 5-10% tolerance

SUPPLY

POLYSEAL PS PG	4 lt
POLYPRIME PS	1 lt pail
POLYPRIME NP	1 lt pail
POLYSOLVENT	5 lt & 20 lt pails
Ancillaries/Equipments	POLYROD

* Refer to website for TDS

4

Apart from the information given here it is also important to observe the relevant guidelines and regulations of various organisations and trade associations as well as the respective standards. The aforementioned characteristics are based on practical experience and applied testing. Warranted properties and possible uses which go beyond those warranted in this information sheet require our written confirmation. All data given was obtained at an ambient and material temperature of +23°C and 50 % relative air humidity unless specified otherwise. Please note that under other climatic conditions hardening can be accelerated or delayed.

The information contained herein, particularly recommendations for the handling and use of our products, is based on our professional experience. As materials and conditions may vary with each intended application, and thus are beyond our sphere of influence, we strongly recommend that in each case sufficient tests are conducted to check the suitability of our products for their intended use. Legal liability cannot be accepted on the basis of the contents of this data sheet or any verbal advice given, unless there is a case of wilful misconduct or gross negligence on our part. This technical data sheet supersedes all previous editions relevant to this product.

Manufactured in G.C.C.



Henkel Polybit Industries Ltd.
P.O. Box 48539, Sharjah, United Arab Emirates
Sales Tel:+971 6 572 2282, Fax:+971 6 572 2289
Factory Tel:+971 6 767 0777, Fax:+971 6 767 1669

Henkel Polybit Industries Ltd.(Branch)
P.O. Box 2230, Al Khobar 31952, K.S.A
Tel:+9663 8894110, Fax:+9663 8995313

Internet: www.henkelpolybit.com E-mail: polybit@henkelpolybit.com

Quality for Professionals

